





# Mood

Cat. A


Polyurethane 3% - Cotton 25% - PVC 72%  
Flame retardant - 50.000 Martindale



1




2




3




4




5



6



7



8




9




10



11



12



13



14



15



16




17



18




19



20



21



22



23



24



25



26



27



28

## Technical details

Composition	Polyurethane 3% - Cotton 25% - PVC 72%
Weight	Gr. /mq. 690 +/- 3%
Abrasion test	Martindale - UNI EN ISO 5470-2/03 50.000 turns
Lightfastness	Xenotest UNI EN ISO 105 B02: 6
Colour fastess to rubbing	Wet: 4/5 Dry: 4/5 Alcool: 4
Resistance Qvtest	UNI EN ISO 105: 6
Flame retardant	IMO resolution A.652 (16): 1989 BS 5852 CRIB 5 BS 5852-1 PART I EN 1021-2 UNI 9175 CLASSE 1 IM TB 117 sez. E – p.1 (California)
Treatment	Mood is treated with VINYZENE, an antimicrobial and Anti-mould agent certified by <b>Bio-Pruf</b>