

Tonus Meadow

Cat. Extra


90% New wool - 10% Helanca
Flame retardant - 100.000 Martindale




115



116



125



126



165



166



225



226



265



266



445



446




465



466



575



576



675



676



715



716



915



916



975



976

Technical details

Composition	90% New wool - 10% Helanca
Weight	Gr. / ml. 665
Abrasion test	Martindale - UNI EN ISO 12947:2000 100.000 rubs
Lightfastness	Xenotest UNI EN ISO 105-B02: 6-7
Flame retardant	BS 5852 Crib 5 with treatment BS 5852 part 1 DIN 4102 B2 EN 1021-1/2 IMO A.652(16) NF D 60 013 NFPA 260 ÖNORM B1/ Q1 SN 198 898 5.3 with treatment
Sustainability	Natural fibres / Sustainable resource