




Extrema

Cat. B

Polyurethane 63% - Cotton 37%  
Flame retardant - 150.000 Martindale




150



250



550




350



1150




2350



650



750



1250



1350



2850



2750



850



950



1050



1650



2450



1550



1450



450



2550



1850



2650



1950



1750



2050



2150



2250

Technical details

Composition	Polyurethane 63% - Cotton 37%
Weight	Gr. /mq. 480
Abrasion test	Martindale - UNI EN ISO 12947-2/2000 150.000 rubs
Lightfastness	Xenotest UNI EN ISO 105 B02: 5-6
Solidity to sweat	UNI EN ISO 105 E04/98: Acid/Alkaline: 4-5
Tropical test	70°C - Days 60 - Unchanged
Flame retardant	BS 5852 CRIB 5 BS 5852-1 PART I IMO resolution A.652 (16): 1989 EN 1021-2 UNI 9175 classe 1 IM TB 117 sez.E – p.1 (California)
Treatment	ULTRA-FRESH / Antimicrobial - Antiacarus It determines durable hygienic freshness